



TECHNICAL DATA SHEET

UG-04 is blown white PE film which the main material is C4-Linear Low Density Polyethylene.

FEATURE

- 1) UG-04 can provide some strength and flexibility to the pouch.
- 2) Hot filling: It is possible to use at 80 °C or less.
- 3) Refrigeration, chilling and freezing conditions.
- 4) Requires protection the product from sunlight.

USE

Snack and General purpose.

General Physical property of White LLDPE-C4 sealable

Description		Unit	Specification				Test Method
Width		mm	Order +5,-0				UPI Method
Length		m	Order 0,+3%				
Thickness		um	25-39 ±7%	40-59 ±5%	60-99 ±4%	100-180 ±3%	
Tensile Strength	MD	MPa	≥ 20				ASTM D 882 /JIS K 7127
	TD		≥ 15				
Elongation at Break	MD	%	≥ 400				
	TD		≥ 600				
Opacity		%	≥ 65				ASTM D 1003
Kinetic COF : Non Treated side		-	0.05 - 0.2				ASTM D 1894/JIS K 7125
Heat seal strength		Kgf/15mm	*				UPI Method
Corona Treated :	Non-Treated	Dynes	None				
	Inside-Treated		38-44				
Color of Film		-	White				
Gel	Number	pcs./m ²	10				
	Size Ø	mm	0.5-1.0				
Black spot	Number	pcs./m ²	5				
	Size Ø	mm	0.1-0.5				
Remark.*Refer to the table 1.							

Table 1 Heat seal strength

Thickness (um)	Temperature(C °)	Unit	Specification	Test Method
25-30	150	kgf/15mm	≥ 0.7	UPI Method
31-49			≥ 0.8	
50-70			≥ 1.0	
71-79			≥ 1.5	
80-99	170		≥ 2.0	
100-120				
121-129				
130-140	180		≥ 2.5	
141-200				

Note :

Raw Material : Linear Low Density Polyethylene, Low Density Polyethylene, slip agent, antiblock agent, processing aid and white masterbatch.

Statutory and regulatory : Complies with U.S. FDA : 21 CFR part 177.1520, RoHS,Commission Regulation (EU) No 10/2011.

The Notification of the Ministry of Public Health (No.435) B.E. 2565 (2022)

Updated Date : 30/4/2026

Page 1/2

Effective date : 08/07/2024

FM-RND-027 Rev.00

บริษัท ยูนิคพลาสติก อินดัสตรี จำกัด (มหาชน) | UNIQUE PLASTIC INDUSTRY PUBLIC COMPANY LIMITED

323 หมู่ 2 ถ.พุทธรักษา ต.โพธิ์รักษาใหม่ อ.เมืองสมุทรปราการ จ.สมุทรปราการ 10280 : Tel: +66 (0) 2 703 6471-6 I Fax: +66 (0) 2 703 6477, 7640

323 Moo 2, Phuttharaksa Rd., Phraek Sa Mai, Mueang Samut Prakan, Samut Prakan, Thailand 10280 : www.uniqueplastic.com

TECHNICAL DATA SHEET

Appearance :	The film shall be uniform ; free of pin hole , foreign matter and streaks.
Storage :	Store in dry place, high temperature not over 40 °C, keep away from direct sunlight, high moisture and fuel gas from LPG gas.
Product guarantee :	The physical properties is not over a year. The change in color of film The change in color of film or appearance is not over six months. The corona treatment and COF property is not over three months from the date of manufacture.

Roll Characteristics.

Width tolerance	:	(+5, -0)mm.(measure on film)
Internal Core diameter	:	76 (+3 , -0) mm.
Joint	:	1 for 20% maximum of total delivery.
Number of joint	:	Maximum 1 joint/roll with red tape.
Film Appearance	:	The film shall be uniform ; free of pin hole , foreign matter and streaks. No creasing , no swollen roll. No corrugation , no blocking. Misalignment is not over 2 mm.

Packaging.



A



B




C



D


A . Horizontal for laminate film




B. Vertical for laminate film



C. Hanging horizontal for shipping and airfreight



D. Horizontal for Heavy duty sack



Roll Identification:

Each roll is identified with label stuck on the roll.

There is information including customer name , width , length , thickness , weight , corona treatment , etc.

The production history can monitor on batch number 15 digits described below;

AA	BB	CC	DDDDDD	- EEE
↓	↓	↓	↓	↓
Type of sale order	Production year	Production month	Number of sale order	Roll Number

Approved by (Customer) :

Position :

Company :

Date :