



TECHNICAL DATA SHEET

UM-50 is a stretched polyethylene film that offers excellent printability and good thermal resistance. The film is corona treated on one side (inner side of the roll) to enhance surface adhesion.

FEATURE

- 1) UM-50 is stiffness, high transparency MDO PE film and heat resistance at 130 °C.
- 2) Possible through the replacement of other types of materials, such as PP, PET or PA, which also makes the packaging recyclable.

USE

FULL PE Packaging.

General Physical property of MDO PE

Description		Unit	Specification	Test Method
Width		mm	Order +5,-0	UPI Method
Length		m	Order 0,+3%	
Thickness		um	23±7%	
Tensile Strength	MD	MPa	≥60	ASTM D 882 /JIS K 7127
	TD		≥15	
Elongation at Break	MD	%	≥50	
	TD		≥200	
Water Vapor Transmission Rate		g.m ² /day	≤10	ASTM F-1249 (90.0%RH and 38.0 °C)
Kinetic COF : Non Treated side		-	≥0.3	ASTM D 1894/JIS K 7125
Haze		%	≤10	ASTM D 1003
Corona Treated :	Non-Treated	Dynes	None	UPI Method
	Treated		38-42	
Color of Film		-	Clear	
Gel	Number	pcs./m ²	10	
	Size Ø	mm	0.5-1.0	
Black spot	Number	pcs./m ²	5	
	Size Ø	mm	0.1-0.5	

Note :

Raw Material : Polyethylene

Statutory and regulatory : Complies with U.S. FDA : 21 CFR part 177.1520, RoHS, Commission Regulation (EU) No 10/2011.

The Notification of the Ministry of Public Health (No.435) B.E. 2565 (2022)

Updated Date : 13/5/2026

Page 1/2

FM-RND-027 Rev.00

Effective date : 08/07/2024

TECHNICAL DATA SHEET

Appearance :	The film shall be uniform ; free of pin hole , foreign matter and streaks.
Storage :	Store in dry place, high temperature not over 40 °C, keep away from direct sunlight, high moisture and fuel gas from LPG gas.
Product guarantee :	The physical properties is not over a year. The change in color of film The change in color of film or appearance is not over six months. The corona treatment and COF property is not over three months from the date of manufacture.

Roll Characteristics.

Width tolerance	:	(+5, -0)mm.(measure on film)
Internal Core diameter	:	76 (+3 , -0) mm.
Joint	:	1 for 20% maximum of total delivery.
Number of joint	:	Maximum 1 joint/roll with red tape.
Film Appearance	:	The film shall be uniform ; free of pin hole , foreign matter and streaks. No creasing , no swollen roll. No corrugation , no blocking. Misalignment is not over 2 mm.

Packaging.

☐

A

☐

B


☐

C

☐

D


A . Horizontal for laminate film




B. Vertical for laminate film



C. Hanging horizontal for shipping and airfreight



D. Horizontal for Heavy duty sack



Roll Identification:

Each roll is identified with label sticked on the roll.

There is information including customer name , width , length , thickness , weight , corona treatment , etc.

The production history can monitor on batch number 15 digits described below;

AA	BB	CC	DDDDDD	- EEE
↓	↓	↓	↓	↓
Type of sale order	Production year	Production month	Number of sale order	Roll Number

Approved by (Customer) :
Position :
Company :
Date :