



TECHNICAL DATA SHEET

US-11 Film is blown white PE film, the main material is linear low density polyethylene blend with high density polyethylene to improve rigidity and make the pouch get more standability which is suitable for detergent packaging bag.

FEATURE

- 1) High rigidity and good heat sealability.
- 2) Good resistance to chemical.
- 3) Requires protection the product from sunlight.

USE

Form fill to seal for stand up pouch liquid detergent and/or others.

General Physical property of White PE Standing Pouch (Roll Form)

Description		Unit	Specification				Test Method
Width		mm	Order +5,-0				UPI Method
Length		m	Order 0,+3%				
Thickness		um	40-59 ±5%	60-99 ±4%	100-139 ±3%	140-180 ±3%	
Tensile Strength	MD	MPa	≥ 20	≥ 20	≥ 20	≥ 22	ASTM D 882 /JIS K 7127
	TD		≥ 15	≥ 15	≥ 15	≥ 20	
Elongation at Break	MD	%	≥ 400	≥ 500	≥ 700	≥ 700	
	TD		≥ 600	≥ 700	≥ 800	≥ 800	
Opacity		‰	≥ 65				ASTM D 1003
Kinetic COF : Non Treated side		-	0.10 - 0.25				ASTM D 1894/JIS K 7125
Heat seal strength		Kgf/15mm	*				UPI Method
Corona Treated :	Non-Treated	Dynes	None				
	Inside-Treated		38-44				
Color of Film		-	White				
Gel	Number	pcs./m ²	10				
	Size Ø	mm	0.5-1.0				
Black spot	Number	pcs./m ²	5				
	Size Ø	mm	0.1-0.5				
Remark.*Refer to the table 1.							

Remark.*Refer to the table 1.

Table 1 Heat seal strength

Thickness (um)	Temperature(C °)	Unit	Specification	Test Method
25-30	150		≥ 0.7	UPI Method
31-49			≥ 0.8	
50-70			≥ 1.0	
71-79			≥ 1.5	
80-99	170		≥ 2.0	
100-120				
121-129				
130-140	180		≥ 2.5	
141-200				

Note :

Raw Material : Linear Low Density Polyethylene, Low Density Polyethylene, Slip agent, Antiblock agent, Processing aid and white masterbatch

Statutory and regulatory : Complies with U.S. FDA : 21 CFR part 177.1520, RoHS, Commission Regulation (EU) No 10/2011.

The Notification of the Ministry of Public Health (No.435) B.E. 2565 (2022)

Updated Date : 30/4/2026

Page 1/2

Effective date : 08/07/2024

FM-RND-027 Rev.00

TECHNICAL DATA SHEET




Appearance :	The film shall be uniform ; free of pin hole , foreign matter and streaks.
Storage :	Store in dry place, high temperature not over 40 °C, keep away from direct sunlight, high moisture and fuel gas from LPG gas.
Product guarantee :	The physical properties is not over a year. The change in color of film The change in color of film or appearance is not over six months. The corona treatment and COF property is not over three months from the date of manufacture.

Roll Characteristics.

Width tolerance	:	(+5, -0)mm.(measure on film)
Internal Core diameter	:	76 (+3 , -0) mm.
Joint	:	1 for 20% maximum of total delivery.
Number of joint	:	Maximum 1 joint/roll with red tape.
Film Appearance	:	The film shall be uniform ; free of pin hole , foreign matter and streaks. No creasing , no swollen roll. No corrugation , no blocking. Misalignment is not over 2 mm.

Packaging.

☐ A
 ☐ B
 ☐ C
 ☐ D

A . Horizontal for laminate film 	B. Vertical for laminate film 
C. Hanging horizontal for shipping and airfreight 	D. Horizontal for Heavy duty sack 

Roll Identification:

Each roll is identified with label stuck on the roll.

There is information including customer name , width , length , thickness , weight , corona treatment , etc.

The production history can monitor on batch number 15 digits described below;

AA	BB	CC	DDDDDD	- EEE
↓	↓	↓	↓	↓
Type of sale order	Production year	Production month	Number of sale order	Roll Number

Approved by (Customer) :
 Position :
 Company :
 Date :